

OptiLite 75 Xtra

Spectrally Selective
Solar Control Film

Optical and Solar Properties:

Visible Light Transmitted	76%
Visible Light Reflected (interior)	9%
Visible Light Reflected (exterior)	9%
UV Radiation Rejected	99%
Total Solar Energy Reflected	8%
Total Solar Energy Transmit.	39%
Total Solar Energy Absorbed	53%
Shading Coefficient	0.63
Emissivity (room side)	0.84
U-value (winter)	1.04
Glare reduction	16%
Solar Heat Gain Coefficient	0.54
Luminous Efficacy Constant	1.23
IR Rejection at 780-2500 nm	88%
IR Rejection at 900-1000 nm	88%
Total Solar Energy Rejected	46%
Item Number	R09275X

Performance results are calculated on 3mm glass using NFRC methodology and LBNL Window 5.2 software, and are subject to variations in process conditions within industry standards and are only intended for estimating purposes.

Hanita Coatings RCA Ltd
Kibbutz Hanita, 22885, Israel
Tel: +972 4 9859919
Fax: +972 4 9859920

solar@hanitacoatings.com | www.hanitacoatings.com



Hanita Coatings