

OMEGA PLUS

Installation-friendly
Automotive films for
the discerning customer

Optical and Solar Properties:	Omega Plus 05	Omega Plus 15	Omega Plus 20	Omega Plus 35	Omega Plus 45
Visible Light Transmitted	5%	15%	24%	35%	44%
Visible Light Reflected	7%	6%	7%	7%	8%
Ultra Violet Block	99%	99%	99%	99%	99%
Total Solar Energy Reflected	9%	7%	8%	8%	8%
Total Solar Energy Transmitted	16%	27%	31%	39%	45%
Total Solar Energy Absorbed	75%	66%	61%	53%	47%
Shading Coefficient	0.43	0.53	0.56	0.64	0.69
Total Solar Energy Rejected	64%	54%	51%	44%	40%
Product code	R059J0A	R058I9A	R058I6A	R058I5A	R058I7A

Performance results are calculated on 6mm glass using NFRC methodology and LBNL Window 5.2 software, and are subject to variations in process conditions within industry standards and are only intended for estimating purposes.

Hanita Coatings RCA Ltd
Kibbutz Hanita, 22885, Israel
Tel: +972 4 9859919
Fax: +972 4 9859920

solar@hanitacoatings.com | www.hanitacoatings.com



Hanita Coatings