


Solar Bronze 35 Xtra

OPTICAL & SOLAR PROPERTIES

	Single Pane	Double Pane
Visible Light Transmitted	33 %	30 %
Visible Light Reflected (Int)	28 %	32 %
Visible Light Reflected (Ext)	30 %	31 %
Ultra Violet Block	99 %	99 %
Total Solar Energy Reflected	52 %	53 %
Total Solar Energy Transmitted	21 %	18 %
Total Solar Energy Absorbed	27 %	29 %
Emissivity (Room Side)	0.84	0.84
Glare Reduction	64 %	63 %
Shading Coefficient	0.33	0.27
Solar Heat Gain Coeff. (G-Value)	0.29	0.23
U-Value Winter (IP)	1.04	0.48
U-Value Winter (SI)	5.91	2.73
Luminous Efficacy	0.97	1.10
Total Solar Energy Rejected	71 %	77 %

R069B5X - Solar Bronze 35 Xtra Pressure Sensitive Adhesive



Ed-B DS No 1507 August 2011