



Automotive

Hybrid Films

Cool Crystal 12

OPTICAL & SOLAR PROPERTIES

| | |
|--------------------------------|------|
| Visible Light Transmitted | 14 % |
| Visible Light Reflected | 6 % |
| Ultra Violet Block | 99 % |
| Total Solar Energy Reflected | 8 % |
| Total Solar Energy Transmitted | 28 % |
| Total Solar Energy Absorbed | 64 % |
| Shading Coefficient | 0.55 |
| Total Solar Energy Rejected | 52 % |

R053Q9A

