

IR 75

Front Cabin Films

OPTICAL & SOLAR PROPERTIES

Visible Light Transmitted	76%
Visible Light Reflected	9%
Ultra Violet Block	99%
Total Solar Energy Reflected	7%
Total Solar Energy Transmitted	40%
Total Solar Energy Absorbed	53%
Shading Coefficient	0.65
Total Solar Energy Rejected	44%

R069IRM

R123IRM* with 4 mil Safety



Powered by
NanoTechnology

Performance results are calculated on 1/4" (6mm) clear glass using NFRC methodology and LBNL Window 5.2 software, and are subject to variations in process conditions within industry standards

Automotive, DS No 1940/2, July 2015

automotive

solar zone



Hanita Coatings