

# 11 mil Clear

## MECHANICAL PROPERTIES

Thickness	11 mil
Tensile Strength at Break	28,500 PSI
Break Strength	308 lb/inch
Elongation at Break	125 %
Peel Strength	7 lb/inch

## OPTICAL & SOLAR PROPERTIES

	3mm Single
Visible Light Transmitted	87%
Visible Light Reflected (Int)	11%
Visible Light Reflected (Ext)	11%
Ultra Violet Block	99%
Total Solar Energy Reflected	10%
Total Solar Energy Transmitted	78%
Total Solar Energy Absorbed	12%
Glare Reduction	3%
Shading Coefficient	0.94
Solar Heat Gain Coeff. (G-Value)	0.82
U-Value Winter (IP)	1.07
U-Value Winter (SI)	6.07
Total Solar Energy Rejected	18%

R29805T PS

Ed-B DS, No 1263, March 2013