

4 mil Alpha Plus Safe 05

MECHANICAL PROPERTIES

Thickness	4 mil
Tensile Strength at Break	28,500 PSI
Break Strength	112 lb/inch
Elongation at Break	125 %
Peel Strength	5-7 lb/inch

OPTICAL & SOLAR PROPERTIES

	6mm Single
Visible Light Transmitted	5%
Visible Light Reflected	7%
Ultra Violet Block	99%
Total Solar Energy Reflected	9%
Total Solar Energy Transmitted	18%
Total Solar Energy Absorbed	73%
Shading Coefficient	0.44
Total Solar Energy Rejected	62%

R125H0A PS

Ed-E DS No 1405, March 2010