

## 4 mil Alpha Plus Safe 20

### MECHANICAL PROPERTIES

Thickness	4 mil
Tensile Strength at Break	28,500 PSI
Break Strength	112 lb/inch
Elongation at Break	125 %
Peel Strength	5-7 lb/inch

### OPTICAL & SOLAR PROPERTIES

	6mm Single
Visible Light Transmitted	19%
Visible Light Reflected	7%
Ultra Violet Block	99%
Total Solar Energy Reflected	8%
Total Solar Energy Transmitted	30%
Total Solar Energy Absorbed	62%
Shading Coefficient	0.55
Total Solar Energy Rejected	52%

R125H6A PS

EG-E DS No 1410, July 2006